

Amendments

In accordance with 37 CFR §1.121, please amend the above-identified application as set forth below.

Amendments to the Specification:

At page 5, line 7-9,

“The polyurethane gel is preferably produced from raw materials having an isocyanate functionality and a functionality of the polyol component with a product of at least 5.2, but preferably of at least 6.5 or 7.5.”

At page 5, line 17-27,

“In a further specific exemplary embodiment, the raw materials for producing the gel includes one or more polyisocyanates, and a polyol component consisting of first component of one or more polyols having hydroxyl numbers below 112, and a second component of one or more polyols having hydroxyl numbers in the range 112 to 600, and optionally a catalyst for the reaction between isocyanate and hydroxyl groups, and optional fillers and/or additives which are known from polyurethane chemistry, wherein the weight ratio of first component to the second component lies between 90:10 and 10:90, the isocyanate characteristic of the reaction mixture lies in the range from 15 to 59.81, and the product of isocyanate functionality and functionality of the polyol component is at least 6.15.”